



COUNTERFORM

CONCRETE COUNTERTOP SOLUTIONS

Z Aqua-Thane M35

Product Description

Z Aqua-Thane M35™ is a water-borne, two-component, self cross linking polyurethane coating. It exhibits a satin finish and offers superior stain, abrasion and chemical resistance. The durability makes this sealer ideal for high-traffic areas. Z Aqua-Thane M35 is safe for indoor or outdoor use.

Features and Benefits

- Provides a matte/ satin, abrasion resistant finish.
- Excellent chemical resistance.
- UV Resistant
- Fast drying

Typical Application

Z Aqua-Thane M35 is recommended as a primer or finish coat on properly prepared concrete surfaces. This may include stained or dyed floors, concrete countertops, overlays/microtoppings, and ornamental concrete. It is food safe and safe for indoor or outdoor use. Z Aqua-Thane M35 does not typically wet out (darken) concrete as much as its solvent based counterparts, thus can be more favorable when color change is not desired.

Technical Information

Gloss 60.....	less than 10	VOC.....	< 75 grams/liter
Pendulum Hardness	1 day 35 s, 7 day 3 min	Mix Ratio.....	4 parts A to 1 part B
Heat Resistance	300°F	Coverage	50-75 sq. ft. / 1.25 quart kit
Water Resistance	Excellent	Pot Life	45 minutes
Chemical Resistance.....	see below	Dry Time-Set to touch (50% R.H. @ 72 F).....	1.5 hours
Solids % Weight (Federal Spec. TTP-141B)	32%	Dry Time-Recoat (50% R.H. @ 72 F).....	4-8 hours
		Dry Time-Light Traffic (50% R.H. @ 72 F).....	24 hours
		Dry Full Time-Cure (50% R.H. @ 72 F).....	3-5 days

Chemical & Stain Resistance (ASTM D-1308 24 Hour Spot Test)

Toluene	No Effect	Urine	No Effect
Ethanol	No Effect	Motor Oil	No Effect
Sulfuric Acid (10%)	No Effect	Transmission Fluid	No Effect
Acetic Acid (3%)	No Effect	Wine	No Effect
Mustard	No Effect	Coffee	No Effect

Coverage

Application Surface

Prepped Concrete

Distance

50-75 sq. ft. @ 2 coats (one 1.25 qt. kit)

*Coverage will vary depending on surface porosity and texture. Excessive build up should be avoided.

Instructions

Surface Prep: New concrete must be completely cured before applying this sealer. Any moisture remaining in the concrete can cause adhesion issues. You can check the concrete with either a moisture meter or by taking several 6x6 inch sheets of clear plastic and thoroughly taping it to the surface completely around the edges. If after 24 hrs the plastic is dry, it is assumed there are not hydrostatic pressure problems. If acid stains or washes are used, the concrete must be completely neutralized back to a pH of 7. On all new hard troweled concrete a light sanding with 100-200 grit sand paper is recommended to open the surface and promote adhesion. On burnished, highly polished or concrete cast against smooth surfaces, additional sanding or acid etching may be required for the best adhesion properties. On textured or stamped concrete, no additional steps are required but in all cases concrete should be clean and 100% free of all dust, debris, or previous coatings.

Mixing: Mix exactly 4 parts of A to 1 part of B. Mix thoroughly with a paint mixing stick and always scrape the sides of your mixing container to ensure a uniform mixture. Mix adequately for 2-3 minutes. Failure to properly mix components may result in adhesion or hardness issues. Pot life of mixed components is roughly 45 minutes to 1 hour at 75°F.

Application: Concrete surface should be between 55°F and 85°F. In smaller areas such as countertops, a 1/4" nap roller or a micro-fiber applicator pad is recommended. Product should be applied in a thin even coating. Do not allow to puddle in low areas. Back rolling may be necessary to control thickness and guarantee a uniform coating. Two coats of sealer should provide sufficient protection. On rough or more porous concrete, additional coats may be needed. Always test concrete with water to confirm concrete is adequately sealed. Recoat time is between 4-8 hours at 75°F and the first coat should be tack free. If this window is missed, the first coat may have to be lightly sanded with 300 grit paper before applying a second coat.

Clean-Up and Removal

All tools and sprayer can be cleaned with xylene or similar solvent prior to end of pot life. Dispose of containers in accordance with local and federal regulations. Dried, cured product may be removed with a commercial stripper, but recommended removal is by way of mechanical means, including sanding, shotblasting, etc.

Precautions and Limitations

- Z Aqua-Thane M35 will not freeze during storage, however, allow temperature to rise to a minimum of 50 °F prior to application.
 - Coverage rates depend upon many conditions including application method, surface porosity, applicator, etc.
 - Be aware this product may be slippery when wet. Anti-slip additive may be needed to reduce slip hazard on certain surfaces.
- If applying over an existing colored surface, proper adhesion and compatibility tests are essential. When using this product, the substrate preparation, application, performance and all other liabilities are strictly the end users responsibility. CCS and it's affiliates offers no guaranty, warranty or other claims to the success or results from the use of this product. CCS warrants the product to be free of defects and will replace or refund the purchase price of the product in the case that said products are proven defective. Any consequential damages including any labor costs are not covered by this warranty and are therefore not recoverable from the manufacturer or associated reseller.